BOSS® 334 Gun Grade Foam

SO

Door & Window Foam

TYPICAL PROPERTIES	
Density	1.56 lbs./ft ³
Thermal Conductivity	0.22 - 0.26 Btu-in/hr-F-ft ²
R Value	3.8 - 4.8 per inch
Tack Free (1" bead)	8 minutes (68°F & 65% RH)
Fully Cured (1″ bead)	12 hours (68°F & 65% RH)
Cuttable (1" bead)	1 hour (68°F & 65% RH)
Tensile Strength	15 psi
Shear Strength	7 psi
Elongation	20%
Yield / 24 Oz. Can	11 gallons freely foamed
Theoretical Yield 24 Oz. 1/4" bead	4300 ft.
Theoretical Yield 24 Oz. 1/2" bead	1030 ft.
VOC	166 g/l
Service Temperature	-40°F to 194°F
Application Temperature	40°F to 95°F

DESCRIPTION

BOSS® 334 Window & Door Minimal Expanding Gun Foam is a one-component, ready to use polyurethane foam, formulated to seal the gap around window and door frame and the rough opening. BOSS® 334 expands to generate an effective seal, and when used properly is proven not to distort or bow window and door frames. **BOSS® 334** will achieve a Sound Transmission Class (STC) of 58 when applying it in accordance with ASTM C-919 "Standard Practice for use of Sealants in Acoustical Applications".

FEATURES

- AAMA 812-04 approved
- CFC propellant free
- Excellent adhesion on most substrates (except Teflon, PE and PP)
- High thermal and acoustical insulation
- Very good filling capacities
- Excellent mounting capacities

HOW TO USE

Surfaces must be clean and free of grease and dust. Spray mist into cavity prior to applying foam and in between layers to improve adhesion and speed up curing. Shake can vigorously for 30 seconds before use and regularly during use for maximum yield. Can must be held **UPSIDE DOWN** during application. Flip open cap and wear gloves provided inside cap. Unclip nozzle. Point nozzle and press trigger. Fill void 50% full to allow for expansion. For best results, use in temperatures between 41°F to 95°F.

SPECIFICATIONS


- ASTM E-2112
- ASTM E-283
- ASTM E-331
- ASTM E-547

- Excellent stability (no shrink or post expansion)
- Very precise application due to the foam gun system
- Low pressure build, reducing the chance of bowing
- VOC Compliant

• ASTM C-1620

• AAMA 812

ASTM E-84 UL 723





Continued...





APPLICATIONS

- Installing of window and doorframes
- Filling of cavities
- Sealing of all openings in roof construction
- Creation of a soundproof screen
- Connecting of insulating materials and roof construction
- Application of a soundproofing layer on motors

Page 1 of 2

Information on this data sheet is subject to change without notice and should not be used for writing specifications. For additional information on specific applications contact Soudal Accumetric.

BOSS® 334 Gun Grade Foam





Uncured sealant can be easily removed using BOSS® 335 or a solvent such as alcohol or acetone. For an environmental and health friendlier choice use BOSS® 893 Biggie Wipes. If the sealant is cured it must be removed mechanically by cutting and scraping.

SHIPPING LIMITATIONS

Ground shipments only. Cannot ship by air. | Reactive VOC 164 g/l (16.4% wt.)

CAUTION

EXTREMELY FLAMMABLE. CONTENTS UNDER PRESSURE. Turn off all pilot lights, electrical igniters, burners and other sources of ignition or heat during use. Do not smoke, use matches or lighters while dispensing foam. Do not expose to direct sunlight, high heat or store in enclosed vehicle. Avoid breathing vapor/spray. Use only outdoors or in a well ventilated area with appropriate breathing apparatus. Avoid contact with skin and eyes. Wearing eyewear and gloves is recommended. Do not incinerate or puncture can. Store at temperatures below 120°F. **KEEP OUT OF REACH OF CHILDREN.** For safe handling information on this product, consult the Safety Data Sheet (SDS).

FIRST AID: In case of eye contact, flush immediately with water for 15 minutes and get medical help. If inhalation causes physical discomfort, move to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help. If swallowed, drink large quantities of water. DO NOT induce vomiting. GET PHYSICIAN ASSISTANCE IN ALL CASES. Cured foam is not harmful to health.

CONTAINS: Polymethylene polyphenyl isocyanate, Dimethylether, Isobutane and Propane

STORAGE AND SHELF LIFE

When stored upright in a dry environment at or below 70°F (21°C), **BOSS® 334** has a shelf life of 12 months from date of shipment. In countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the cap pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.



- 12 oz. Straw Can
- 20 oz. Genius Can
- 24 oz. Gun Grade Can



Limited Warranty: Buyer assumes all risks of use, handling and storage of product not in strict accordance with label directions. Liability for any incidental or consequential damage or loss is specifically excluded at all times. Any implied warranty of merchantability or fitness for particular use is excluded. Seller will not accept liability for more than product replacement.



Soudal Accumetric

MADE IN BELGIUM

350 Ring Road Elizabethtown, KY 42701 800-928-BOSS(2677) 270-769-3385 FAX 270-765-2412 www.bossproducts.com

BOSS is a registered trademark of Soudal

BOSS® 334 Straw Foam



TECHNICAL DATA SHEET

Door & Window Foam

TYPICAL PROPERTIES	
Density	1.56 lbs./ft ³
Thermal Conductivity	0.22 - 0.26 Btu-in/hr-F-ft ²
R Value	3.8 - 4.8 per inch
Tack Free (1″ bead)	8 minutes (68°F & 65% RH)
Fully Cured (1″ bead)	12 hours (68°F & 65% RH)
Cuttable (1" bead)	1 hour (68°F & 65% RH)
Tensile Strength	15 psi
Shear Strength	7 psi
Elongation	20%
Yield / 24 Oz. Can	4.9 gallons freely foamed
Theoretical Yield 12 Oz. 1/4" bead	1500 ft.
Theoretical Yield 12 Oz. 1/2" bead	480 ft.
VOC	235 g/l
Service Temperature	-40°F to 194°F
Application Temperature	40°F to 95°F

DESCRIPTION

BOSS® 334 Window & Door Minimal Expanding Straw Foam is a one-component, ready to use polyurethane foam, formulated to seal the gap around window and door frame and the rough opening. BOSS® 334 expands to generate an effective seal, and when used properly is proven not to distort or bow window and door frames. BOSS® 334 will achieve a Sound Transmission Class (STC) of 58 when applying it in accordance with ASTM C-919 "Standard Practice for use of Sealants in Acoustical Applications".

FEATURES

- AAMA 812-04 approved
- CFC propellant free
- Excellent adhesion on most substrates (except Teflon, PE and PP)
- High thermal and acoustical insulation
- Very good filling capacities
- Excellent mounting capacities

HOW TO USE

Surfaces must be clean and free of grease and dust. Spray mist into cavity prior to applying foam and in between layers to improve adhesion and speed up curing. Shake can vigorously for 30 seconds before use and regularly during use for maximum yield. Can must be held **UPSIDE DOWN** during application. Flip open cap and wear gloves provided inside cap. Unclip nozzle. Point nozzle and press trigger. Fill void 50% full to allow for expansion. For best results, use in temperatures between 41°F to 95°F.

SPECIFICATIONS

- ASTM E-2112
- ASTM E-283
- ASTM E-331
- ASTM E-547

• ASTM C-1620

expansion)

gun system

of bowing

VOC Compliant

• Excellent stability (no shrink or post

• Very precise application due to the foam

• Low pressure build, reducing the chance

- ASTM E-84 UL 723
- AAMA 812

- APPLICATIONS
 - Installing of window and doorframes
 - Filling of cavities
 - Sealing of all openings in roof construction
 - Creation of a soundproof screen
 - Connecting of insulating materials and roof construction
 - Application of a soundproofing layer on motors

Scan the QR Code to see the full line of **BOSS**PRO Products!



Continued...



BOSS® 334 Straw Foam





Uncured sealant can be easily removed using BOSS[®] 334 or a solvent such as alcohol or acetone. For an environmental and health friendlier choice use BOSS[®] 893 Biggie Wipes. If the sealant is cured it must be removed mechanically by cutting and scraping.

SHIPPING LIMITATIONS

Ground shipments only. Cannot ship by air. | Reactive VOC 175 g/l (17.9% wt.)

CAUTION

EXTREMELY FLAMMABLE. CONTENTS UNDER PRESSURE. Turn off all pilot lights, electrical igniters, burners and other sources of ignition or heat during use. Do not smoke, use matches or lighters while dispensing foam. Do not expose to direct sunlight, high heat or store in enclosed vehicle. Avoid breathing vapor/spray. Use only outdoors or in a well ventilated area with appropriate breathing apparatus. Avoid contact with skin and eyes. Wearing eyewear and gloves is recommended. Do not incinerate or puncture can. Store at temperatures below 120°F. **KEEP OUT OF REACH OF CHILDREN.** For safe handling information on this product, consult the Safety Data Sheet (SDS).

FIRST AID: In case of eye contact, flush immediately with water for 15 minutes and get medical help. If inhalation causes physical discomfort, move to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help. If swallowed, drink large quantities of water. DO NOT induce vomiting. GET PHYSICIAN ASSISTANCE IN ALL CASES. Cured foam is not harmful to health.

CONTAINS: Polymethylenepolyphenylisocyanate, Dimethylether, Isobutane and Propane

STORAGE AND SHELF LIFE

When stored upright in a dry environment at or below 70°F (21°C), **BOSS® 334** has a shelf life of 12 months from date of shipment. In countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the cap pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

TECHNICAL DATA SHEET

COLORS

• Tan

PACKAGING

- 12 oz. Straw Can
- 20 oz. Genius Can
- 24 oz. Gun Grade Can



SURFACE BURNING CHARACTERISTICS Applied To Increase Residue And Anton Tensor to Sard-FLAME SPREAD: 15 / SMOKE DEVEloPED: 35 Covering 11. percent of the request test sample area. DUNING CHARACTERISTICS INCODENCENTIF CANOLC-STO2 Applied To Increasing: Reinforced Cament Bardy FLAME SPREAD: 30 / SMOKE DEVELOPED: 50 40 applied 11 w 25 min dimension between and and an applied 11 w 25 min dimension between and an applied 11 w 25 min dimension between and and an applied 11 w 25 min dimension between and an applied 11 w 25 min dimension between and an applied 11 w 25 min dimension between and an applied 11 w 25 min dimension between an applied 11 w 25 min dimension between and an applied 11 w 25 min dimension between an a

Limited Warranty: Buyer assumes all risks of use, handling and storage of product not in strict accordance with label directions. Liability for any incidental or consequential damage or loss is specifically excluded at all times. Any implied warranty of merchantability or fitness for particular use is excluded. Seller will not accept liability for more than product replacement.



Soudal Accumetric

MADE IN BELGIUM

350 Ring Road Elizabethtown, KY 42701 800-928-BOSS(2677) 270-769-3385 FAX 270-765-2412 www.bossproducts.com

BOSS is a registered trademark of Soudal

BOSS® 334 Genius Gun® Foam



TECHNICAL DATA SHEET

Door & Window Foam

TYPICAL PROPERTIES	
Density	1.56 lbs./ft ³
Thermal Conductivity	0.22 - 0.26 Btu-in/hr-F-ft ²
R Value	3.8 - 4.8 per inch
Tack Free (1″ bead)	8 minutes (68°F & 65% RH)
Fully Cured (1″ bead)	12 hours (68°F & 65% RH)
Cuttable (1" bead)	1 hour (68°F & 65% RH)
Tensile Strength	15 psi
Shear Strength	7 psi
Elongation	20%
Yield / 24 Oz. Can	6.6 gallons freely foamed
Theoretical Yield 20 Oz. 1/4" bead	2279 ft.
Theoretical Yield 20 Oz. 1/2" bead	557 ft.
VOC	175 g/l
Service Temperature	-40°F to 194°F
Application Temperature	40°F to 115°F

DESCRIPTION

BOSS® 334 Genius Gun® Window & Door Minimal Expanding Foam is a one-component, ready to use polyurethane foam, formulated to seal the gap around window and door frame and the rough opening. **BOSS® 334** expands to generate an effective seal, and when used properly is proven not to distort or bow window and door frames. **BOSS® 334** will achieve a Sound Transmission Class (STC) of 58 when applying it in accordance with ASTM C-919 "Standard Practice for use of Sealants in Acoustical Applications".

FEATURES

- AAMA 812-04 approved
- CFC propellant free
- Excellent adhesion on most substrates (except Teflon, PE and PP)
- High thermal and acoustical insulation
- Very good filling capacities
- Excellent mounting capacities

HOW TO USE

- Excellent stability (no shrink or post expansion)
- Very precise application due to the foam gun system
- Low pressure build, reducing the chance of bowing
- VOC Compliant

Surfaces must be clean and free of grease and dust. Spray mist into cavity prior to applying foam and in between layers to improve adhesion and speed up curing. Shake can vigorously for 30 seconds before use and regularly during use for maximum yield. Can must be held **UPSIDE DOWN** during application. Flip open cap and wear gloves provided inside cap. Unclip nozzle. Point nozzle and press trigger. Fill void 50% full to allow for expansion. For best results, use in temperatures between 41°F to 95°F.

SPECIFICATIONS

- ASTM E-2112
- ASTM E-283
- ASTM E-331
- ASTM E-547

- ASTM C-1620
- ASTM E-84 UL 723
- AAMA 812



Patent No. 10,106,309,B2

APPLICATIONS

- Installing of window and doorframes
- Filling of cavities
- Sealing of all openings in roof construction
- Creation of a soundproof screen
- Connecting of insulating materials and roof construction
- Application of a soundproofing layer on motors

Scan the QR Code to see the full line of **BOSS**^{PRO} Products!





BOSS® 334 Genius Gun® Foam





Uncured sealant can be easily removed using BOSS® 335 or a solvent such as alcohol or acetone. For an environmental and health friendlier choice use BOSS® 893 Biggie Wipes. If the sealant is cured it must be removed mechanically by cutting and scraping.

SHIPPING LIMITATIONS

Ground shipments only. Cannot ship by air. | Reactive VOC 175 g/l (18% wt.)

CAUTION

EXTREMELY FLAMMABLE. CONTENTS UNDER PRESSURE. Turn off all pilot lights, electrical igniters, burners and other sources of ignition or heat during use. Do not smoke, use matches or lighters while dispensing foam. Do not expose to direct sunlight, high heat or store in enclosed vehicle. Avoid breathing vapor/spray. Use only outdoors or in a well ventilated area with appropriate breathing apparatus. Avoid contact with skin and eyes. Wearing eyewear and gloves is recommended. Do not incinerate or puncture can. Store at temperatures below 120°F. **KEEP OUT OF REACH OF CHILDREN.** For safe handling information on this product, consult the Safety Data Sheet (SDS).

FIRST AID: In case of eye contact, flush immediately with water for 15 minutes and get medical help. If inhalation causes physical discomfort, move to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help. If swallowed, drink large quantities of water. DO NOT induce vomiting. GET PHYSICIAN ASSISTANCE IN ALL CASES. Cured foam is not harmful to health.

CONTAINS: Polymethylenepolyphenylisocyanate, Dimethylether, Isobutane and Propane

STORAGE AND SHELF LIFE

When stored upright in a dry environment at or below 70°F (21°C), **BOSS® 334** has a shelf life of 12 months from date of shipment. In countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the cap pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.



COLORS

• Tan

PACKAGING

- 12 oz. Straw Can
- 20 oz. Genius Can
- 24 oz. Gun Grade Can



Limited Warranty: Buyer assumes all risks of use, handling and storage of product not in strict accordance with label directions. Liability for any incidental or consequential damage or loss is specifically excluded at all times. Any implied warranty of merchantability or fitness for particular use is excluded. Seller will not accept liability for more than product replacement.



Soudal Accumetric

MADE IN BELGIUM

350 Ring Road Elizabethtown, KY 42701 800-928-BOSS(2677) 270-769-3385 FAX 270-765-2412 www.bossproducts.com

BOSS is a registered trademark of Soudal